

310 Austenitic Stainless Steel Bar

Typical Composition		Min.	Max.
	Carbon		0.15%
	Silicon		1.50%
	Manganese		2.00%
	Chromium	24.00%	26.00%
	Nickel	19.00%	22.00%
	Phosphorus		0.04%
	Sulphur		0.030%
Related Specifications			
	AISI 310		
	ASTM A276-92-310		
	BS970 Part 3: 1991-310S31		
	AS 2837-1986-310		
310 is designed for continuous high temperature service in the range 850 - 1000°C. May be weakly magnetic.			
For further technical information, please contact our sales office.			
	Available on an indent basis only		

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.