



ENGINEERING STEELS + ALLOYS



## BRONZE BUSHING LG2

Available in continuous cast bar and hollow sections, see stocked sizes.

### Related Specifications

AS C83600 AS.1565-1985 C83600

BS.1400 LG2

ASTM 836

SAE 40

### Typical Composition

	Min. %	Max. %
Copper	84	86
Tin	4	6
Zinc	4	6
Lead	4	6
Phosphorous		.05
Aluminium		.005

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.