


BRONZE BUSHING PB1 (PHOSPHOUR BRONZE)

Colour Code



Yellow (Bar End)

Related Specifications

A.S.T.M. 1565-1985 904D

B.S. 1490 PB1

S.A.E. 65

Commonly used for gears, bearings and heavy load bushes.

Typical Composition

| | Min. % | Max. % |
|-------------|-----------|--------|
| Copper | Remainder | |
| Tin | 10.20 | 12.00 |
| Zinc | | 0.05 |
| Nickel | | 0.10 |
| Lead | | 0.25 |
| Phosphorous | | 1.20 |
| Aluminium | | 0.005 |
| Iron | | 0.10 |

Interloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.