


BRONZE BUSHING PB1 (PHOSPHOUR BRONZE)

Colour Code



Yellow (Bar End)

Related Specifications

A.S.T.M. 1565-1985 904D

B.S. 1490 PB1

S.A.E. 65

Commonly used for gears, bearings and heavy load bushes.

Typical Composition

	Min. %	Max. %
Copper	Remainder	
Tin	10.20	12.00
Zinc		0.05
Nickel		0.10
Lead		0.25
Phosphorous		1.20
Aluminium		0.005
Iron		0.10

Interloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.