

## BRONZE BUSHING PB2 (PHOSPHOUR BRONZE)

Available subject to enquiry

### Related Specifications

A.S. 1565-1985 907C

B.S. 1490 PB2

S.A.E. 65

Commonly used for gears, worm wheels and where shock resistance is required

### Typical Composition

	Min. %	Max. %
Copper	Remainder	
Tin	11.20	13.00
Zinc		0.30
Nickel		0.50
Lead		0.25
Phosphorous	0.15	0.80
Aluminium		0.005
Iron		0.15
Magnese		1.00

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.