

EN36A CASE HARDENING STEEL

EN36A is a 3.2% nickel - chromium high hardenability, case hardening (carburizing) steel, generally supplied in the annealed condition with a maximum brinell hardness of 255 (Rc26). Characterised by high core strength, excellent toughness and fatigue resistance in relatively large sections with case hardness up to Rc62 when carburized, hardened and tempered. Characterised by high core strength, excellent toughness and fatigue resistance in relatively large sections with case hardness up to Rc62 when carburized, hardened and tempered. EN36A can also be used (uncarburized) as a high tensile steel, which when suitably hardened and tempered can be utilized for various applications requiring good tensile strength and excellent toughness. Pre hardened and tempered (uncarburized) EN36A can be further surface hardened by nitriding but will not respond satisfactorily to flame or induction hardening due to its low carbon content. EN36A (carburized) is used extensively by all industry sectors for components and shafts requiring high surface wear resistance, high core strength and impact properties. Typical uses are: Heavy Duty Bushings, Collets, Conveyor Pins, Heavy Duty Gears, King Pins, Ring Gears, Sprockets, Shafts etc..

Colour Code	Stocked Sizes	
	Rounds	14mm to 610 mm Diameter
	Bar Finish	
	Peeled, Turned or Hot Rolled	

Related Specifications

Australia	AS 1444-1996-X3312/X3312H
Germany	W.Nr 1.5752 DIN 14NiCr14
Great Britain	BS970: PART 3: 1991 655 M13 BS970: 1955 - EN36A
Japan	JISG 4052 SNC815H JISG 4102 SNC815
USA	SAE 3310 9310 AISI E3310 E9310 UNS G33106/G93106

Chemical Composition

	Min. %	Max. %
Carbon	0.10	0.16
Silicon	0.10	0.40
Manganese	0.35	0.60
Nickel	3.00	3.75
Chromium	0.70	1.00
Phosphorous	0	0.04
Sulphur	0	0.04

Mechanical Property Requirements - As Supplied to AS1444-1996 X3312

Annealed Condition - Brinell Hardness 255 Maximum

Mechanical Property Requirements - As Supplied to BS 970 Part 3-1991 655M13

Test Bar Diameter mm		19
Tensile Strength Mpa	Min	1000

Elongation 5.65√S ₀ %	Min	9		
Izod Impact J	Min	40		
Charpy Impact J	Min	35		
*Annealed Brinell Hardness	Max	255		
<p>Note: Mechanical tests are in the blank carburised condition Hardening Temperature 800°C - 820°C *Hardness figures are in the condition stated.</p>				
Typical Mechanical Properties - Annealed				
Tensile Strength Mpa		700/770		
Yield Strength Mpa		540		
Elongation on 5.65√S ₀ %		25		
Hardness	HB	212		
	Rc	17		
Typical Mechanical Properties For Core - Carburised and Oil Quenched at 830°C.				
Section Size mm		11	30	63
Tensile Strength Mpa	Min	1030	930	880
	Max	1320	1230	1180
Yield Strength Mpa	Min	835	785	735
Elongation on 5.65√S ₀ %	Min	9	10	10
Charpy Impact J	Min	55	55	
Hardness HB	Min	300	275	260
	Max	385	360	350
Hardness Rc	Min	33	29	27
	Max	42	40	39
Typical Mechanical Properties - Oil Quenched at 830°C and Tempered as Indicated *				
Tempering Temperature °C		200	430	650
Tensile Strength Mpa		1140	1080	726
Yield Strength Mpa		896	865	540
Elongation on 5.65√S ₀ %		20	20	25
Izod Impact J		95	95	135
Hardness	HB	340	320	212
	Rc	37	35	17
<p>*Section Size 50 mm EN36A is however generally used in the carburised condition with heat treatment details as follows.</p>				
Forging				
<p>Heat to 1150°C and hold until temperature is uniform throughout the section. Soaking time at forging temperature should be as short as possible to avoid heavy scaling and excessive grain growth. This will vary depending on furnace conditions but 15 minutes per 25 mm of section may be used as a guide. Do not forge below 850°C. Following completion of forging operation, work piece should be cooled as slowly as possible in sand or dry lime etc. Note: Case hardening steels due to their low carbon content are less susceptible to cracking than medium or high carbon steels, and may therefore be heated and cooled more rapidly.</p>				
Heat Treatment				
Annealing				
Heat to 830°C - 850°C, hold until temperature is uniform throughout the section and cool in furnace.				
Carburizing				
Pack, salt or gas carburize at 900°C - 950°C, holding for sufficient time to develop the required case depth and carbon content, followed by a suitable hardening and tempering cycle to optimise case and core properties.				
Hardening				

Refer Refining & Hardening.

Nitriding

EN36A suitably hardened and tempered (uncarburised) will respond to nitriding giving a surface hardness up to Rc 60. Nitriding is carried out at 490°C - 530°C followed by slow cooling (no quench), reducing the problem of distortion.
N.B. The fairly high nickel content in EN36A will result in a lower case hardness, or a longer nitriding cycle than with other alloy grades containing less nickel.

Normalizing - For Improved Machinability

Heat to 880°C - 920°C, hold until temperature is uniform throughout the section. Soak for 10 - 15 minutes and cool in still air. Temper immediately at 650°C - 660°C and air cool.

Refining & Hardening

Core Refine

Slow cool from carburizing temperature and re-heat to 830°C - 880°C, hold until temperature is uniform throughout the section, quench as required in water, oil or air cool. Alternatively quench in salt bath held at 150°C - 250°C, followed by air cool.

Case Hardening

Following core refining, re-heat to 760°C - 800°C, hold until temperature is uniform throughout the section, and quench in oil. Temper immediately while still hand warm.

Single Refine*

Direct Quench: Cool from carburizing temperature to 810 °C - 830 °C, hold until temperature is uniform throughout the section. Quench as required in water, oil or air cool. Alternatively quench in salt bath held at 150 °C - 250 °C, followed by air cool and temper immediately.

Or: Cool from carburizing temperature to room temperature, re-heat to 810 °C - 830 °C and hold until temperature is uniform throughout the section and quench or air cool as previous. Temper immediately.

Note: When air cooling large sections a uniform fan cooling is recommended, especially when direct cooling from carburizing temperature.

*Suitable for fine grained steels only.

Stress Relieving

Heat to 600°C - 650°C, hold until temperature is uniform throughout the section, soak for 1 hour per 25 mm section, and cool in still air.

Tempering

Heat to 150°C - 200°C as required, hold until temperature is uniform throughout the section, soak for 1 - 2 hours per 25 mm of section, and cool in still air. N.B. Tempering will improve the toughness of both case and core, with only a slight reduction in core strength and case hardness. It will also reduce the susceptibility of the case to grinding cracks.

Notes on Heat Treatment

Heating temperatures, rate of heating, cooling and soaking times will vary due to factors such as work piece size/shape also furnace type employed, quenching medium and work piece transfer facilities etc.. Please consult your heat treater for best results.

Machining

EN36A in the annealed as supplied condition has very good machinability and all operations such as turning, drilling, milling and tapping etc. can be carried out satisfactorily as per machine manufacturers recommendations for suitable tool type - feeds and speeds.

Welding

EN36A is readily weldable in the annealed as supplied condition. Following welding, the work piece immediately upon cooling to hand warm should be stress relieved at 600°C - 650°C if possible. N.B. Welding in the carburized and heat treated condition is not recommended.

Welding Procedure

Welding of EN36A should always be carried out using low hydrogen electrodes - please consult your welding consumables supplier.

Suggested Pre-heat Temperature

Section	25mm	50mm	75mm	150mm
°C	250	300	350	400

Post Welding

Maximum cooling rate 100°C per hour down to 100°C, followed by cooling in still air. It is recommended that the work piece if possible is buried in sand or dry lime etc..

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.