

# DUCTILE IRON 3D

Colour Code

Green

## Typical Mechanical Properties

Material Section	Anticipated Tensile Values N/mm <sup>2</sup>	Hardness(BHN)	Matrix
20 < D ≤ 60	500	170-240	Ferritic - Pearlitic
60 < D ≤ 120	450	170-240	Ferritic - Pearlitic
120 < D ≤ 400	420	170-240	Ferritic - Pearlitic
400 < D ≤ 700	420	170-240	Ferritic - Pearlitic
Stocked Sizes	Available in continuous cast iron bar in sizes 40 - 360 mm diameter.		

## Related Specifications

3D-500-7C, EN16482, EN-GJS-500-7C

A spheroidal graphite cast iron that possesses high elasticity and resistance to impact. 3D has an increased Pearlitic structure, resulting in higher wear resistance and increased strength with improved heat-treatment response. It is recommended for applications in which good machinability and surface finish are required, as well as minimal friction with other parts and/or materials. Suitable for applications involving thermal and mechanical shock. Noise and vibration damping are good in this grade. Conforms EN-16482:2014 EN GJS-500-7C

## Typical Composition

	Min. %	Max. %
Carbon	3.25	3.70
Silicon	2.40	3.00
Manganese	0.10	0.40
Magnesium	0.04	0.07

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.