

GREY IRON 4E

Colour Code

Yellow

Typical Mechanical Properties

Tensile Strength 220-260 MPa

Hardness 170-220 BHN

Stocked Sizes Available in continuous cast bar in sizes:
Round Sizes
Flat Sizes

Related Specifications

AS 1830- 1985 T260

BS 1452 Grade 17

ASTM A48 Classes 35-40

DIN 1691 GG35

JIS FC 25

A free machining grey cast iron, not suitable in applications where surface wear resistance is required.

Typical Composition

	Min. %	Max. %
Carbon	3.00	3.70
Silicon	2.20	2.90
Manganese	0.20	0.70
Copper	0	0.30
Phosphorous		0.10

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.