

4145H MODIFIED HIGH TENSILE STEEL

Chromium/Molybdenum high tensile steel has good ductility, shock resistance and wear resistance. 4145H modified conforms to API Spec 7. Typical uses are: drilled collars, connecting rods, shafts, gears

Colour Code	Stocked Sizes	
Silver/Green(Bar End) 	Rounds	
	Hexagons	
	Hollow Bar	
	Square	
	Bar Finish	
	Peeled, Black Bar	

Related Specifications

Australia	
Germany	
Great Britain	
International	API Spec 7
Japan	
USA	SAE J1268, UNS H41450, ASTM A304

Chemical Composition (Base Material)

	Min. %	Max %
Carbon	0.42	0.49
Silicon	0.15	0.35
Manganese	0.65	1.10
Chromium	0.75	1.20
Molybdenum	0.15	0.25
Phosphorous	0	0.035
Sulphur	0	0.04
Nickel	0	0.25
Copper	0	0.35

Mechanical Property Requirements for Steels in the Heat-Treated Condition for Peeled, Black Bar

Mechanical Property Designation	API - 7	
Limited Ruling Section mm		
Tensile Strength Mpa	Min	970
	Max	
0.2% Proof Stress Mpa	Min	755
Elongation on 5.65√S ₀ %	Min	13

Izod Impact J	Min	
Charpy Impact J	Min	54
Hardness Brinell HB	Min	
	Max	341

Forging

Heat to 1200 °C maximum, hold until temperature is uniform throughout the section. Do not forge below 950 °C.

Heat Treatment

Annealing

Heat to 815 °C - 850 °C, hold until temperature is uniform throughout the section.

Flame or Induction Hardening

Hardening

Heat to 820 °C - 870 °C, hold until temperature is uniform throughout the section. Quench in oil as required.

Nitriding

Normalizing

Heat to 870 °C - 900 °C, hold until temperature is uniform throughout the section, soak for 10 - 15 minutes and cool in still air.

Stress Relieving

Tempering

Re-heat to 430 °C - 700 °C as required and according to properties required.

Notes on Heat Treatment

Machining

Welding

Best results by common fusion or resistance methods. Do not weld by oxyacetylene.

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.