

## BRONZE BUSHING AB2 (ALUMINIUM BRONZE)

Colour Code

Silver/Green (Bar End)

### Related Specifications

Australia	AS1565-1985-C95810
Germany	
Great Britain	BS1490 AB2
International	
Japan	
USA	

### Typical Composition

	Min. %	Max. %
Aluminium	8.50	9.50
Tin		0.10
Manganese	0.80	1.50
Nickel	4.00	5.00
Copper	79.00	
Lead		0.05
Iron	3.50	4.50

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.