


440C MARTENSITIC STAINLESS STEEL BAR

440C is a high carbon straight chromium high hardenability martensitic stainless steel, generally supplied in the annealed condition with a maximum Brinell hardness of 269 (Rc29) or annealed and cold drawn with a maximum Brinell hardness of 285 (Rc31). Characterised by good corrosion resistance in mild domestic and industrial environments, including fresh water, organic materials, mild acids, various petroleum products, coupled with extreme high strength, hardness and wear resistance when in the hardened and tempered condition. 440C due to its excellent hardenability is capable of being through hardened up to Rc60 depending upon carbon content and section size. Small sections can be air cooled and quite large sections oil quenched for maximum through hardness. Used for parts requiring a combination of excellent wear resistance, plus reasonable corrosion resistance. Typical applications are: Ball Bearings and Races, Bushings, Cutlery, Chisels, Knife Blades, Pump Parts, Surgical Instruments, Valve Seats etc.

Material magnetic in all conditions.

Colour Code	Stocked Sizes	
Dark Brown (Bar end)	Stocked Sizes	45 mm to 160 mm diameter.
	Bar Finish	
	Peeled Bar	

Related Specifications

Australia	AS 2837-1986 440C
Germany	W.Nr 1.4125 X105CrMo17
Japan	JIS G4303 SuS 440C
USA	ASTM A276-98b 440C SAE 51440C AISI 440C UNS S44004

Chemical Composition

	Min. %	Max %
Carbon	0.95	1.20
Silicon	0	1.00
Manganese	0	1.00
*Nickel	0	1.00
Chromium	16.00	18.00
Molybdenum	0.00	0.75
Phosphorous	0	0.04
Sulphur	0	0.03

*Nickel addition optional.

Mechanical Property Requirements For Material in the Annealed Condition to 1) AS2837 - 1986 440C and 2) ASTM A276-98b 440C

Specification	AS2837-1986 440C	
Finish		

Brinell Hardness		269 Max						
Capable of attaining Rc59 minimum in 10mm test bar oil quenched from 1010°C - 1070°C.								
Specifrication		ASTM A276-98b 440C						
Finish		Hot Finished	Cold Finished					
Brinell Hardness		269 Max	285 Max					
Capable of attaining Rc58 minimum in 9.50mm test bar air cooled 1020°C.								
Typical Mechanical Properties At Room Temperature in the Annealed Condition (AS Supplied)								
Tensile Strength Mpa		785						
Yield Strength Mpa		420						
Elongation in 50mm %		15						
Impact Charpy J		6						
Hardness	HB	240						
	Rc	24						
Typical Mechanical Properties At Room Temperature - Hardened By Oil Quench at 1030°C and Tempered as Indicated								
Tempering Temperature °C			150	200	250	300	350	400
Tensile Strengt Mpa			2050	2020	1980	1890	1820	1780
Yield Strength Mpa			1930	1896	1845	1760	1675	1635
Elongation in 50mm %			4	4	4	4	4	4
Impact Charpy J			9	9	9	9	9	9
Hardness Rc			60	59	57	56	56	56
Section Size 25mm High tensile strength, high yield strength and high hardness but low impact properties.								
Elevated Temperature Properties								
440C is not generally recommended for elevated temperature applications due to a reduction in corrosion resistance when tempered above 400°C								
Low Temperature Properties								
440C is also not recommended for use at sub-zero temperatures due to a further drop in impact properties.								
Cold Bending								
Moderate cold bending is possible when fully annealed to maximum softness.								
Hot Bending								
Not generally recommended due to the high hardenability - air hardening capabilities of this grade. If really necessary then work piece following operation should be cooled as slowly as possible either in a furnace or in warm dry lime or ashes to room temperature prior to annealing.								
Corrosion Resistance								
440C has a corrosion resistance somewhat similar to 410 grade, but lower than 431 grade, also lower than most of the 400 series ferritic stainless steels and all of the 300 series austenitic stainless steels.NB. It has optimum corrosion resistance in the hardened and tempered condition when tempered below 400°C. Hardening from 1090°C will ensure better carbide solution, and therefore better corrosion resistance, but minimum soaking time should be allowed at this temperature otherwise excessive grain growth can occur. Polishing will further develop its corrosion resistance. It is not recommended for use in the annealed condition.It is most important that oxygen is always allowed to circulate freely on all stainless steel surfaces to ensure that a chrome oxide film is always present to protect it. If this is not the case, rusting will occur as with other types of non stainless steels.								
For optimum corrosion resistance surfaces must be free of scale and foreign particles. Finished parts should be passivated.								
Forging								

Preheat to 760°C - 820°C, then heat slowly and uniformly to 1050°C - 1150°C, hold until temperature is uniform throughout the section and commence forging immediately. Do not overheat as this can cause a loss of toughness and ductility. Do not forge below 900°C. Finished forgings should be cooled slowly in a furnace, warm dry lime or ashes to room temperature and annealed immediately.

NB. Air cooling after forging may cause cracking.

Heat Treatment

Sub-Critical Annealing

Heat uniformly to 730°C - 770°C hold until temperature is uniform throughout the section.

*Soak as required. Cool in air.

Annealing

Heat uniformly to 840°C - 900°C, hold until temperature is uniform throughout the section.

*Soak as required. Cool in furnace.

Hardening

Heat to 1010°C - 1070°C, hold until temperature is uniform throughout the section. *Soak as required. Quench in warm oil or air cool. Do not overheat. Temper immediately while still hand warm. NB. This grade can be hardened from 1090°C for optimum corrosion resistance but this will result in a lower hardness level obtained.

Tempering

Heat to 100°C - 400°C, as required, hold until temperature is uniform throughout the section. *Soak as required. Cool in air. Tempering within the range 100°C - 200°C will give optimum corrosion resistance and maximum hardness - up to Rc60 depending upon section size. NB. Tempering above 400°C is not recommended as it will result in a reduction in corrosion resistance and impact properties. *Heating temperatures, rate of heating, cooling and soaking times will vary due to factors such as work piece size/shape, also furnace type employed, quenching medium and work piece transfer facilities etc.

Please consult your heat treater for best results.

Machining

431 machines best in the hardened and tempered as supplied condition and is regarded as being readily machineable with all operations such as turning and drilling etc. capable of being carried out satisfactorily. It does not work harden to the same extent as the 300 series austenitic stainless steels, but is more similar in this respect to the low alloy high tensile steels such as 4140 etc. Allowing therefore for its high tensile properties, all machining should be carried out as per machine manufacturers recommendations for suitable tool type, feeds and speeds.

Welding

440C due to its high carbon content has low machinability. It machines best in the fully annealed condition and chip curlers and breakers are recommended as chips tend to be strong and stringy. All operations such as drilling, turning and milling etc. should be carried out as per machine manufacturers recommendations for suitable tool type, feeds and speeds.

Grinding and Polishing

440C in the hardened and tempered condition requires care with finish grinding and polishing to avoid overheating as this can lower the hardness and corrosion resistance.

Welding

Welding 440C in the annealed as supplied condition is not recommended due to its high air hardening capability which can lead to the formation of brittle martensite, resulting in cold cracking due to contraction stresses within the weld and heat affected zone.

Welding 440C in the hardened and tempered condition should not be attempted.

If welding is really necessary in the annealed condition the following welding procedure and post-weld heat treatment may be taken as a guide only.

Welding Procedure

Welding electrodes or rods should be low hydrogen types and as *similar to the base metal as possible when high strength is required, otherwise an austenitic stainless *electrode or rod may be used, resulting in a more ductile weld if strength is not so critical. Pre-heat at 260°C and maintain interpass temperature at 260°C minimum. On completion of welding cool slowly as possible to 260°C minimum, followed immediately by: Post-weld sub-critical anneal at 730°C - 770°C or full anneal at 840°C - 900°C and harden and temper as required. *Please consult your welding consumables supplier.

Interlloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.

316L due to its low carbon content has greater resistance to intergranular corrosion than all the austenitic stainless steel grades except

304L grade and 321 titanium stabilized grade.